

*Bitumen 40/50 Specifications*

No.	Analysis	Unit	Limit	Test Method
1	Density@25 °C	Kg/m ³	1010-1060	ASTM D70 or D3289
2	Penetration@25 °C	mm/10	40-50	ASTM D5
3	Softening point	°C	49 Min.	ASTM D36
4	Ductility@25 °C	Cm	100 Min.	ASTM D113
5	Loss on heating	Wt%	0.2 Max.	ASTM D6
6	Drop in penetration after heating	%	20 Max.	ASTM D5
7	Flash point	°C	232 Min.	ASTM D92
8	Solubility in Trichloroethylene	Wt%	99.0 Min.	ASTM D2042
9	Spot test	-	Negative.	AASHTO T102
10	Viscosity@60 °C	P	4000 $\pm$ 800	ASTM D2171
11	Viscosity@135 °C	CST	400 Min.	ASTM D2170

